WHAT IS CLAIMED IS:

1. A segmented polymer comprising one or more soft segments comprising silane-containing groups, wherein the soft segments are derived from a compound of the formula:

$$HO-R^1-Si(R^2)_2-[-R^3-Si(R^2)_2-]_n-R^1-OH$$

wherein:

10

n = 1 or more;

each R¹ is independently a straight chain or branched alkylene group optionally including heteroatoms;

each R² is independently a saturated or unsaturated aliphatic group, an aromatic group, or combinations thereof, optionally including heteroatoms; and

15

each R³ is independently a straight chain alkylene group, a phenylene group, or a straight chain or branched alkyl substituted phenylene group, wherein each R³ optionally includes heteroatoms;

- with the proviso that the polymer is substantially free of carbonate linkages.
 - 2. The polymer of claim 1 which is substantially free of urea linkages.

25

- 3. The polymer of claim 1 wherein n = 1 to 50.
- 4. The polymer of claim 1 wherein each R¹ is independently a straight chain or branched (C3-C20)alkylene group.

30

5. The polymer of claim 1 wherein each R² is independently an alkyl group, a phenyl group, or an alkyl substituted phenyl group.

6. The polymer of claim 5 wherein each R² is independently a straight chain or branched (C1-C20)alkyl group, a phenyl group, or a straight chain or branched (C1-C20)alkyl substituted phenyl group.

÷ :

- 5 7. The polymer of claim 6 wherein each R² is independently a straight chain (C1-C3)alkyl group.
 - 8. The polymer of claim 1 further comprising urethane groups.
- 10 9. The polymer of claim 1 wherein each R³ is independently a (C1-C20)alkylene group.
 - 10. The polymer of claim 1 wherein each R³ is independently a (C4-C12)alkylene group.
 - 11. The polymer of claim 10 wherein each R³ is independently a (C6-C10)alkylene group.
- 12. The polymer of claim 1 with the proviso that when R³ is an
 20 unsubstituted straight chain alkylene group it has more than 4 carbons.
 - 13. The polymer of claim 1 which is a biomaterial.

15

- 14. The polymer of claim 1 which is substantially free of ether andester linkages.
 - 15. The polymer of claim 1 which is linear, branched, or crosslinked.
- 16. The polymer of claim 1 further comprising one or more softsegments derived from a diol that does not contain a silane-containing group.

- 17. The polymer of claim 1 further comprising one or more hard segments derived from a chain extender.
- 18. A medical device comprising a segmented polymer comprising one or more soft segments comprising silane-containing groups derived from a compound of the formula:

$$HO-R^1-Si(R^2)_2-[-R^3-Si(R^2)_2-]_n-R^1-OH$$

10 wherein:

15

20

n = 1 or more;

each R¹ is independently a straight chain or branched alkylene group optionally including heteroatoms;

each R² is independently a saturated or unsaturated aliphatic group, an aromatic group, or combinations thereof, optionally including heteroatoms; and

each R³ is independently a straight chain alkylene group, a phenylene group, or a straight chain or branched alkyl substituted phenylene group, wherein each R³ optionally includes heteroatoms;

with the proviso that the polymer is substantially free of carbonate linkages.

- 19. The medical device of claim 18 wherein the segmented polymer25 is substantially free of urea linkages.
 - 20. The medical device of claim 18 wherein n = 1 to 50.
- 21. The medical device of claim 18 wherein each R¹ is independently a straight chain or branched (C3-C20)alkylene group.
 - 22. The medical device of claim 18 wherein each R² is independently an alkyl group, a phenyl group, or an alkyl substituted phenyl group.

- 23. The medical device of claim 22 wherein each R² is independently a straight chain or branched (C1-C20)alkyl group, a phenyl group, or a straight chain or branched (C1-C20)alkyl substituted phenyl group.
- 24. The medical device of claim 23 wherein each R² is independently a straight chain (C1-C3)alkyl group.
- 25. The medical device of claim 18 further comprising urethanegroups.

5

20

30

- 26. The medical device of claim 18 wherein each R³ is independently a (C1-C20)alkylene group.
- 15 27. The medical device of claim 18 wherein each R³ is independently a (C4-C12)alkylene group.
 - 28. The medical device of claim 27 wherein each R³ is independently a (C6-C10)alkylene group.
 - 29. The medical device of claim 18 with the proviso that when R³ is an unsubstituted straight chain alkylene group it has more than 4 carbons.
- 25 30. The medical device of claim 18 wherein the polymer is a biomaterial.
 - 31. The medical device of claim 18 wherein the polymer is substantially free of ether and ester linkages.
 - 32. The medical device of claim 18 wherein the polymer is linear, branched, or crosslinked.

- 33. The medical device of claim 18 wherein the polymer further comprises one or more soft segments derived from a diol that does not contain a silane-containing moiety.
- 5 34. The medical device of claim 18 wherein the polymer further comprises one or more hard segments derived from a chain extender.
 - 35. A segmented polymer comprising one or more soft segments comprising silane-containing groups of the formula:

 $-R^{1}-Si(R^{2})_{2}-[-R^{3}-Si(R^{2})_{2}-]_{n}-R^{1}-$

wherein:

n = 1 or more;

15 each

10

20

25

each R¹ is independently a straight chain or branched alkylene group optionally including heteroatoms;

each R² is independently a saturated or unsaturated aliphatic group, an aromatic group, or combinations thereof, optionally including heteroatoms; and

each R³ is independently a straight chain alkylene group, a phenylene group, or a straight chain or branched alkyl substituted phenylene group, wherein each R³ optionally includes heteroatoms;

with the proviso that the polymer is substantially free of carbonate linkages.

- 36. The polymer of claim 35 comprising urethane groups.
- 37. A medical device comprising a segmented polymer comprising one or more soft segments comprising silane-containing groups of the formula:

$$-R^{1}-Si(R^{2})_{2}-[-R^{3}-Si(R^{2})_{2}-]_{0}-R^{1}-$$

wherein:

5

10

15

30

n = 1 or more;

each R¹ is independently a straight chain or branched alkylene group optionally including heteroatoms;

each R² is independently a saturated or unsaturated aliphatic group, an aromatic group, or combinations thereof, optionally including heteroatoms; and

each R³ is independently a straight chain alkylene group, a phenylene group, or a straight chain or branched alkyl substituted phenylene group, wherein each R³ optionally includes heteroatoms;

with the proviso that the polymer is substantially free of carbonate linkages.

- 38. The medical device of claim 37 wherein the segmented polymer comprises urethane groups.
- 39. A method of making a segmented polymer, the methodcomprising: combining a polyisocyanate with a compound of the formula:

$$HO-R^1-Si(R^2)_2-[-R^3-Si(R^2)_2-]_n-R^1-OH$$

wherein:

n = 1 or more;

each R¹ is independently a straight chain or branched alkylene group optionally including heteroatoms;

each R² is independently a saturated or unsaturated aliphatic group, an aromatic group, or combinations thereof, optionally including heteroatoms; and

each R³ is independently a straight chain alkylene group, a phenylene group, or a straight chain or branched alkyl substituted

phenylene group, wherein each R³ optionally includes heteroatoms;

with the proviso that the polymer is substantially free of carbonate linkages.

5

40. The method of claim 39 wherein the segmented polymer comprises urethane groups.